

Chicken Feather Waste As Adsorbent for Crude Oil Clean Up From Crude Oil Polluted Water

*¹A. A. OKOYA, ²N. O. OCHOR, ³A. B. AKINYELE, ⁴O. O. OLAIYA

ABSTRACT—This study assessed the adsorption potentials of chicken feather waste (CFW) in Nigeria for the crude oil removal from crude oil polluted water (CPW) in comparison with commercial activated carbon (CAC). This was with a view to providing information on the efficacies of the CFW as an adsorbent. The pulverized chicken feathers were characterized using Rutherford Backscattering Spectrometer (RBS) and Scanning Electron Microscope (SEM) for elemental composition and the determination surface morphology, respectively. Factors such as initial concentration, adsorbent dosage, pH, and contact time were optimized using standard methods. The batch adsorption experiments were carried out for the removal of crude oil from CPW using the CFW and CAC. The data obtained were subjected to one-way analysis of variance. The elemental composition of the CFW showed the presence of Na, Mg, Al, P, K, Ca, Ti, Cr, Mn, Fe, Cu, Zn, Sr, Zr, Cd, Sn, Pb and Si within the range 12.8 - 22566.3 ppm with agglomeration of particle. There was distinctive irregular morphology with large surface area of the CFW. CAC exhibited a high percentage removal efficiency ranging from 88.51 to 96.75%, while CFW ranged from 99.76 to 99.95% for crude oil removal for all initial concentrations (1/3 to 5/3 v/v crude oil/water). Best adsorbent dosage for the crude oil removal for CFW was 25 g, at 50 min contact time, pH 12 and 5/3 (v/v crude oil /water) initial concentration. The order of percentage removal efficiencies of the crude oil by the adsorbents were CFW (98.20 – 99.95) > CAC (82.63 – 95.08). The study concluded that chicken feathers could be an effective adsorbent for the removal of crude oil from crude oil polluted water.

Index Terms—Agriculture, Chicken feathers, Oil pollution, Adsorption.

I. INTRODUCTION

The WHO [1] reported that as a result of high population growth in Africa and growing income, the demand for eggs and poultry meat, in recent year, has significantly increased across most parts of the continent. According to the USAID (United States Agency for International Development) estimates, this trend is likely to continue over the next few years. As a result, the consumption of poultry and eggs will increase by 200% between 2010 and 2020 for at least some countries in sub-Saharan Africa as reported by [2] and [3]. Nigeria is an African country where this trend can clearly be seen. Nigeria is one of the largest and most populous country

¹ *Institute of Ecology and Environmental Studies, Obafemi Awolowo University, Ile-Ife, Nigeria, ronkeokoya@yahoo.com,

² Dept of Forestry and Environmental Management, Micheal Okpara University of Agriculture, Umudike, Nigeria, sanenelly@gmail.com

³ Institute of Ecology and Environmental Studies, Obafemi Awolowo University, Ile-Ife, Nigeria, bankypraise82@gmail.com

⁴ Institute of Ecology and Environmental Studies, Obafemi Awolowo University, Ile-Ife, Nigeria, oolalekan852@gmail.com

in Africa, with a total geographical area of 923,768 square kilometers [4]. Its estimated population was 174.5 million people in 2013, and its population growth rate is 3% per annum [3].

Nigerian economic statistics reveal annual economic growth rates that averaged over 7% in recent decades, making Nigeria one of the fastest growing economies in the world [2]. Nonetheless, this growth has not reduced poverty or created much needed jobs. According to [5], unemployment is still very high, and more than 60% of the population lives below the poverty line.

However, the Nigerian poultry industry in particular as reported by [3]; [6] has been rapidly expanding in recent years and is therefore one of the most commercialized (capitalized) subsectors of Nigerian agriculture. Hence, the popularity of poultry production can be as result of the fact that poultry has many merits over other livestock. Poultry birds better converters feed into useable protein inform meat and eggs. The production costs per unit is relatively low, and the return on investment is high. Therefore, farmers need a comparatively small capital to start a poultry farm. Furthermore, poultry meat is very tender and acceptability to consumers is high, regardless of their religious beliefs. Also, capital is not tied up over a long period because the production cycle is quite short . Finally, eggs which are one of the major products of poultry production, are relatively affordable for the common person than other sources of animal protein [7]; [8].

On the other hand, oil pollution, can be as a result of natural disaster like earthquake, volcanic eruption, hurricane etc., or as a result of man's interference for example terrorism, oil bunkering, tanker and oil rig accidents, to mention but a few. It is a prominent occurrence in oil producing countries like Nigeria which therefore result to a concern on how to attend to the challenges of oil pollution in the environment. This is because of the various impacts it has on the aquatic and terrestrial environment.

Different methods have been developed such as adsorption, absorption, ion exchange, coagulation etc for the removal of different contaminants such as spent engine oil, urban storm water runoff, bacteria, virus and fungi from different sewage pipes etc but not without limitations. The commercial activated carbon (CAC) have been in use as adsorbent for crude oil removal from the water environment but very expensive, hence the need to develop cheaper and environment friendly adsorbents from some agricultural waste which could constitute nuisance in the environment. Many researchers have developed such agricultural wastes as adsorbents for solving oil pollution problems. [9], reported that several natural organic sorbents have been studied for the removal of oil spill, for example raw sugar cane bagasse [10]; [11]; and [12], raw and fatty-acid grafted sawdust for oil [13] and other pollutants [14], black and white rice husk ash [15], barley straw [16], banana trunk fibers [17], acetylated sugarcane bagasse [18]; [19], carbonized peat bagasse [16] peat-based sorbents [20], and hydrophobic aerogels for emulsified oil [21]; [22].

Adsorption is a surface phenomenon which involves the adhesion of atoms, ions, or molecules from a gas, liquid, or dissolved solid to a surface [23]. Despite the report of several studies carried out on the use of agricultural waste as adsorbent, there is paucity of information on the use of chicken feather waste (CFW) for removal of crude oil from crude oil polluted water (CPW), hence this study.

II. MATERIALS AND METHODOLOGY

A. Sample Collection and Preparation

The agricultural wastes used for this study was chicken feathers. The CFW was sourced from a local market at Ile-Ife, Osun State Nigeria, while commercial activated carbon (Calgon Activated Carbon) was purchased from Uche-El Water Limited, Olowo Complex, Iwo Road, Ibadan, Oyo State also in Nigeria. The CFW was immersed in detergent-containing tap water to remove stains, oil and grease, and then rinsed with the tap water. The chicken feathers were rinsed with distilled water to remove any detergent left and sun-dried to constant weight. After that, chicken feathers were pulverized (plate 1) with ROCKLABS Ring mill pulverizer Model CRC3E; Serial no 1288 at the Center for Energy, Research and Development (CERD), Obafemi Awolowo University, Nigeria. The pulverized feathers were used directly because it could not be passed through the sieves due to its fibrous nature.

B. Characterization of Chicken Feather

The pulverized CFW was characterized using Scanning Electron Microscopy (SEM) and Particle-induced X-ray Emission (PIXE). (equipment model) from Centre for Energy Research and Development (CERD)

C. Simulation of Crude Oil polluted water

The CPW was prepared in the laboratory by mixing 20 ml of crude oil with 30 ml deionized water in a 250 ml beaker and shaken with a digital orbital shaker (JINOTECH INSTRUMENTS), for a period of 20 mins at a constant speed of 300 rpm. The CPW was then used for the adsorption experiment using different adsorbent dosages, contact times, initial concentrations, pH.

D. Batch Adsorption of Crude oil using the Chicken Feather Waster

Twenty grams of each of the adsorbents (pulverized CFW and CAC) was added to the crude oil polluted water (20 ml) in a beaker in turns. The beakers and its contents were placed on a digital orbital shaker (JINOTECH INSTRUMENTS), and shaken at 300 rpm for 20 mins. The contents of the beakers were then filtered to separate the wetted adsorbent from the filtrate. The weight of the wetted adsorbent was recorded and the weight of the filtrate (oil and water) as well as the separated water from the filtrate were recorded separately. Adsorbed oil content was determined by subtracting the water content and the initial adsorbent weight from the total wetted sorbent. The weight of the oil adsorbed was then recorded as gg^{-1} (gram of oil/gram of adsorbent).

Batch adsorption experiments were carried out twice, and the mean recorded for the different adsorbent dosages, contact time, pH and concentration. The data obtained were subjected to One-way ANOVA. One-way ANOVA is used to analyze the distribution of one factor among several independent groups or means.

The percentage of oil adsorbed was calculated using the equation (3.1).

$$\frac{wf - wi}{wi} \quad (3.1)$$

Where:

w_i is the initial weight of crude oil (ml/ml) before adsorption

w_f is the final weight of crude oil (ml/ml) in the filtrate after adsorption.



Figure 1: Pulverized chicken feathers

III. RESULTS AND DISCUSSION

A. Characterization of the Adsorbents

The results for the characterization of pulverized CFW are presented below:

a. Elemental composition of the adsorbent

The presence of these elements (Na, Mg, Al, Si, P, K, Ca, Ti, Cr, Mn, Fe, Cu, Zn, Sr, Zr, Cd, Sn, Pb) characterized using Rutherford Backscattering Spectrometer (RBS) as shown in Table 1 in the CFW can enhance adsorption through the following mechanism: biosorption, ion exchange, chelation, co-ordination and complexation reactions. Elements like Al, K, Na, Ca and Mg could have influence on the adsorption mechanism through biosorption and ion exchange interaction, that is, by exchanging with metal ions present in the aqueous solution [24], while the presence of such elements as P and Si according to [25] and [26] could influence adsorption through the chelation, coordination and complexation.

b. Surface Morphology of Chicken feathers

In the results of Scanning Electron Microscopy, Fig. 1 compared the surface morphology before (a) and after (b) adsorption process of the CFW respectively.

Furthermore, the results of the scanning electron microscope clearly showed the surface texture and morphological characteristics of CFW. The magnification was optimized at a display magnification of more than 2000 times. Agglomeration of particles of CFW (as shown in fig. 1a and 1b) and the distinctive irregular material which is in line with the works of [27] and [28] is said to enhance adsorption.

Fig. 1a and 1b show the agglomeration of particles, and the non-availability of toxic element in the composition of the sorbent materials which in turn support their uses for effluent treatments as reported by [29].

Table 1: Elemental composition of Chicken feathers

Element	Conc. (ppm)	Conc. Error
---------	-------------	-------------

Na	376.3	±22.11
Mg	795.8	±43.53
Al	699.6	±40.11
Si	1858.1	±57.07
P	7546.7	±101.50
K	1104.7	±70.46
Ca	22566.2	±81.64
Ti	376.0	±12.23
Cr	564.0	±30.12
Mn	291.9	±31.44
Fe	18363.0	±26.36
Cu	5373.6	±24.38
Zn	4139.4	±18.51
Sr	17.5	±3.31
Zr	84.8	±11.20
Cd	77.3	±10.38
Sn	91.0	±11.32
Pb	12.8	±4.0

Furthermore, the results of the scanning electron microscope clearly showed the surface texture and morphological characteristics of CFW. The magnification was optimized at a display magnification of more than 2000 times. Agglomeration of particles of CFW (as shown in Fig.s 1a and 1b) and the distinctive irregular material which is in line with the works of [27] and [28] is said to enhance adsorption.

Fig.s 1a and 1b show the agglomeration of particles, and the non-availability of toxic element in the composition of the sorbent materials which in turn support their uses for effluent treatments as reported by [29].




Figure 2: SEM images of chicken feathers (a) before adsorption and (b) after adsorption

B. Adsorption Studies on Crude oil Using CFW and CAC

The parameters affecting the adsorption were studied by comparing the adsorbents. Effects of these parameters are presented below:

a. Effect of Adsorbent Dosage on Adsorption of Crude Oil from Crude Oil Polluted Water

The result of the experiment for the adsorption of crude oil using CFW from crude oil polluted water is presented in Fig. 2. The adsorption efficiencies ranged from 72.55 to 99.33 and from 41.75 to 82.63 for CFW and CAC respectively with varying dosages of 5, 10 15 20 and 25g. The mean percentage ($85.4 \pm 4.81\%$) of crude oil adsorbed with CFW is significantly higher than that of CAC ($59.1 \pm 8.02\%$). The adsorption efficiencies increased with increase in adsorbent dosage for both CFW and CAC. This implies that CFW and CAC can be used effectively for crude oil adsorption. The increase in efficiency with increase in adsorbent dosage for the CFW could be due to greater availability of exchangeable sites and increase in surface area at higher dose of the adsorbents respectively. These observations are in line with the findings of previous studies on many other adsorbents [30]; [31]; [9] and [32].

b. Effect of Contact Time on Adsorption of Crude Oil from Crude Oil Polluted Water

The effect of contact time on the removal efficiency of crude oil from CPW is shown in Fig. 3. The adsorption efficiencies ranged from 73.15 to 99.80 and from 68.34 to 92.79 for CFW and CAC respectively with varying contact time (10, 20, 30, 40, 50 minutes). The mean percentage ($85.59 \pm 4.95\%$) of crude oil adsorbed with CFW is significantly higher ($F=17.073$; $P=0.000$) at confidence interval of 0.05) than that of CAC ($83.76 \pm 4.23\%$). The




Figure 3: Effect of Adsorbent Dosage on Adsorption of Crude oil from crude oil polluted water




Figure 4: Effect of Contact Time on Adsorption of Crude oil from crude oil polluted water

Adsorption efficiencies increased as the time increases for both CFW and CAC. It shows that the adsorption of crude oil increases with time and then reaches a constant value beyond which no more oil was further removed from the polluted water. This may be due to the availability of a large number of vacant sites at the beginning of the adsorption experiment. This agrees with work of [33] and [34] who reported that the percentage removal of the adsorbent increase with contact time and constant with increase in contact time. Since all the adsorbent sites exist in the exterior of the adsorbent, it is easy for the adsorbate to access these active sites, resulting in rapid approach of equilibrium [35]. Also [36] reported that the rate of removal of dye increased with an increase in contact time to a certain extent and further increase in contact time does not increase the uptake due to deposition of dyes on the available adsorption site on adsorbent material.

c. Effect of Initial Concentration on Adsorption of Crude Oil from Crude Oil Polluted Water

The results of the investigation of the adsorption of crude oil on the adsorbents with varied initial concentration are presented in Fig. 4. Fig. 4 presents the adsorption efficiencies of CAC and CFW with varied initial concentrations (10/30, 20/30, 30/30, 40/30, and 50/30 ml/ml) for the two adsorbents, while all other conditions (adsorbent dosage, contact time, and pH) were kept constant. The efficiencies of adsorption increased with increasing initial concentration for the two adsorbents except initial concentration of 20/30 which decreased in the case of CAC. For the two adsorbents, the initial concentration which showed the optimum amount of crude oil adsorbed (99.95 % for CFW) from the CPW was 80 ml (50/30 ml/ml). The adsorption efficiencies for all the initial concentrations for the adsorbents is significantly different ($F=16.114$; $P=0.000$) at confidence interval of 0.05. CFW showed greater adsorption efficiency of 99.95 %, followed by CAC which showed an adsorption potential of 95.08% ($P=0.577 > C.I=0.05$). This is in agreement with [37] who reported that initial oil concentration affects removal of oil from wastewater as the initial concentration of oil influences the oil adsorption kinetics and inhibits hydraulic conductivity. In a study by [37] on the removal of oil from palm oil mill effluent (POME) by chitosan, it was discover that chitosan was able to give high oil removal efficiency in

POME with low oil concentration compared with POME of higher oil concentration. It may be that, at high oil concentration, oil occupies the surface of sorbent thus saturation is reached quickly and high amount of unattached oil is left. In terms of filtration mechanism, this phenomenon can be explained by the occupation of spaces between sorbent particles (macropores) by oil, thereby hindering more oil to infiltrate into the sorbent micropores as reported by [38].




Figure 5: Effect of Initial Concentration on Adsorption of Crude oil from crude oil polluted water

d. Effect of pH on Adsorption of Crude Oil from Crude Oil Polluted Water

The pH of effluent can undoubtedly affect the adsorption potential of the adsorbent. The results of the investigation of the adsorption of crude oil on the adsorbents with varied pH of 2.0, 4.0, 10.0, and 12.0 while other conditions (adsorbent dosage, contact time and initial concentration) were kept constant, are presented in Fig. 5.

Fig. 5 shows the effect of pH on the adsorption efficiencies of the adsorbents for the adsorption of crude oil from crude oil polluted water. The range of the adsorption efficiencies for the varying pH values (2, 4, 10, 12) is 72.95 – 84.70 and 85.64 – 98.20 for CAC and CFW respectively. The mean adsorption efficiencies are 79.64 ± 2.74 and 92.29 ± 2.73 for CAC and CFW respectively. The adsorption efficiencies of crude oil at different pH for the adsorbents is significantly different for the adsorbents ($F=11.019$; $P=0.001$) at confidence level of 0.05. The efficiency for CFW is significantly higher (98.20 %) than the CAC (84.70%). The result of the laboratory experiment showed that the pH 12.0 was the best pH favouring the maximum adsorption of crude oil. Also, according to [39], the pH of a solution, in fact determines the chemistry, degree of ionization and speciation of metal ions and also affects the surface charge of the adsorbent. In this study, the adsorption behaviour of crude oil were studied at different pH values. This is because the pH change affects the surface properties and sorbent binding sites [40], and emulsion breaking [41]. A number of studies reported the increase of oil removal in acidic and basic medium. [37] and [41] reported in their studies on chitosans that palm oil and crude oil removal efficiency was increases at strongly acidic and basic pH. According to [37], saponification

process is associated to high removal efficiency at strong basic condition whereby hydrolysis of oil in sorbate occurs.

Several studies demonstrated an increase in oil removal efficiency as the sorbate pH increases. For example, motor oil removal using natural wool fibre revealed high removal efficiency at pH 10, and low removal efficiency at pH 5 [42]. In addition, the use of surfactant-modified barley straw showed the lowest removal efficiency for canola oil and mineral oil at strongly acidic condition (pH 2), with an increase in removal efficiency in parallel to increasing pH as reported by [43]. [40] reported that low oil adsorption at extremely low pH was suggested to occur due to ionisation of the sorbate, which caused lower favourability of oil adsorption.




Figure 6: Effect of pH on Adsorption of Crude oil from crude oil polluted water

IV. CONCLUSION

This study showed that chicken feathers, instead of constituting a nuisance to the environment could be processed to serve as cheaper, non-hazardous alternative adsorbents to the commercially expensive activated carbon for removing crude oil from crude oil polluted water. Best adsorption conditions for chicken feathers are 50:30 initial concentration; 25 g dose; pH 12.0; and 50 min contact time for adsorption of crude oil from crude oil polluted water. The amount of water adsorbed together with crude oil on water is negligible which means that both sorbents; pulverized chicken feathers and standard (commercial activated carbon) can be used in mopping of crude oil spill on water. The result of the study shows that chicken feathers is an efficient sorbent for the mopping of crude oil spill on water. Chicken feathers exhibit a higher adsorption for crude oil to that of commercial activated carbon.

V. RECOMMENDATION

Treatment of crude oil polluted water with agricultural wastes should complement the conventional treatment for efficient removal of crude oil from the polluted water. Government and industries should take advantage of adsorption technologies by developing these natural adsorbents for household purposes.

REFERENCES

1. World Health Organisation. Health and environment in Europe: progress assessment. Copenhagen: WHO Regional office for Europe; . p. 1-168. [28-9-2011. Ref Type: Report], 2010.
2. Obi, E. Educational management: theory and practice. JAMOE Nigeria Enterprises, Enugu, 2003.
3. USDA, N. The plants database. baton rouge la, national plant data center., 2013.
4. Manyong, V.M.; Ikpi, A.; Olayemi, J.K.; Yusuf, S.A. Agriculture in Nigeria: Identifying opportunities for increased commercialization and Investment. IITA Ibadan (p.159 p), 2005.
5. African Economic Outlook. Promoting youth employment. A publication of AfDB, 2012.
6. Adene, D. F.; Oguntade, A.E. The structure and importance of the commercial and village based poultry industry in Nigeria. FAO, Rome, Italy, 2006
7. Ojo, O. Fundamentals of research methods. Standard Publications, Lagos, 2003.
8. Aboki, E.; Aau, J.; Ji, O. Productivity and technical efficiency of family poultry in kurmi local government area of taraba state, nigeria. Journal of agriculture and sustainability. Infinitypress.info
9. Behnood, R., Anvaripour, B., Jaafarzade Haghighi Fard, N., & Farasati, M. Application of natural sorbents in crude oil adsorption. Iranian Journal of Oil & Gas Science and Technology, 2(4), 1-2013.
10. Hussein, E.M.; Hussein, A.M.; Eida, M.M.; Atwa, M.M. Pathophysiological variability of different genotypes of human Blastocystis hominis Egyptian isolates in experimentally infected rats. Parasitology research, Springer, 2008.
11. Said, C.P., Sebe, N., Todorov, A. Structural resemblanceto emotional expressions predicts evaluation of emotionally neutral faces. Emotion 9 (2), 260, 2009.
12. Brandão, P.C.; Souza, T.C.; Ferreira, C.A.; Hori, C.E. Removal of petroleum hydrocarbons from aqueous solution using sugarcane bagasse as adsorbent. Journal of Hazardous Materials 175(1- 3), 1106-1112. Elsevier, 2010.
13. Banerjee, A.K.; Chatterjee, M.; Yu, Y.; Sang-Gon, S; Miller, W.A.; and Hannapel, D.J. 2006. Dynamics of a mobile RNA potato involved in a long- distance signalling pathway. The Plant Cell vol. 18, 3443-3457. American Society of Plant Biologists.
14. Shukla, A.; Zhang, Y.H.; Dubry, P.; Margrave, J.L. and Shukla, S.S. The role of sawdust in the removal of unwanted materials from water. Journal of Hazardous Materials 95 (1-2), 137-152 2002.
15. Vlaev, L., Petkov, P., Dimitrov, A.. Genieva, S. Clean up of polluted water with crude oil or diesel fuel using rice husks ash. Journal of the Taiwan Institute of Chemical Engineers 42 (6), 957-964. 2011.

16. Hussein, K.; Sprecher, H.; Mashiaxh, T.; Oren, I. Carbapenem resistance among *Klebsiella pneumoniae* isolates risk factors, molecular characteristics, and susceptibility patterns. *Journal of infection control and hospital epidemiology* vol.30, No.7. cambridge.org. 2009.
17. Sathasivam, K. and Haris, H. M. Adsorption kinetics and capacity of fatty acid-modified banana trunk fibers for oil in water. *Journal of Water, Air, & Soil Pollution* 213 (1-4), 413-423. 2010.
18. Chung, Y., Tanaka, S., Chu, F., Nurieva, R.I., Martinez, G.J. Follicular regulatory t cells expressing Foxp3 and Bcl-6 suppress germinal center reactions. *Nature medicine* 17 (8), 983. 2011.
19. Sun, T., Xie, W., Xu, P. Superoxide anion scavenging activity of graft chitosan derivatives. *Carbohydrate polymers* 58 (4), 379-382. 2004.
20. Cojocoru, V., Balali-Mood, K., Samsom, M.S.P., Wade, R.C. Structure and dynamics of the membrane-bound cytochrome P450 2C9. *PLoS computational biology* 7 (8), e1002152. 2011.
21. Site, A.D. Factors affecting sorption of organic compounds in natural sorbent/water systems and sorption coefficients for selected pollutants, A review. *Journal of Physical and Chemical Reference Data*. 30 (1), 187-439, 2013.
22. Wang, J., Zheng, Y. and Wang, A. Effect kapok fiber treated with various solvents on oil absorbency. *Industrial Crops and Products*, 40(1), 178-184. 2012.
23. The Brownfield and Land Revitalization Technology Support Center. Retrieved 2009-12-21 Roland Akelsson min-CV-accessed 2008-01-29 from the World Wide Web: <https://brownfieldstsc.org> Assessed on 15/06/2017
24. Volesky, B. (2003). *Biosorption of heavy metals*: CRC press. ISBN 0849349176, 9780849349171. 408pp. Available at <https://www.books.google.com>. Assessed on 14/06/2017.
25. Miessler, G. L. And Tarr, D. A. . *Coordination chemistry iv: reactions and mechanisms*. *Inorganic chemistry*, 384-393. 1999.
26. Lancashire, R. J. *Stability, Chelation and the Chelate Effect*. 2015.
27. Okoya, A. A., Akinyele, A. B., Ifeanyi, E., Amuda, O. S., Alayande, O. S., & Makinde, O. W. Adsorption of heavy metal ions onto chitosan grafted cocoa husk char. *African Journal of Pure and Applied Chemistry*, 8(10), 147-161. 2014.
28. Selvaraju, G. and Bakar, N. K. A. Production of a new industrially viable green-activated carbon from artocarpus integer fruit processing waste and evaluation of its chemical, morphological And adsorption properties. *Journal of Cleaner Production*, 141(1), 989-999. 2017.
29. Alayande, O., Olatubosun, S., Adedoyin, O., Deborah, Olalekan. Porus and non-porous electrospun fibres from discarded expanded polystyrene. *International journal of physical sciences* 7(11), 1832-1836. 2012.
30. Amuda, O., Giwa, A., & Bello, I. Removal of heavy metal from industrial wastewater using modified activated coconut shell carbon. *Biochemical Engineering Journal*, 36(2), 174-181. 2007.
31. Muhammad, I., El-Nafaty, U., Abdulsalam, S., & Makarfi, Y. Removal of oil from oilproduced water using eggshell. *Civil and Environmental Research*, 2(8), 52. 2012.
32. Ijeoma, K. H., & Prisca, U. I. Assessment of Crude Oil Mopping Efficiency of Pulverized Chicken Feathers: Kinetic and Adsorption Isotherm Studies. 2018.

33. Kanyal, M., & Bhatt, A. A. Removal of heavy metals from water (Cu and Pb) using household waste as an adsorbent. *Journal of Bioremediation & Biodegradation*, 6(1), 1-6. 2015.
34. Mateen, F., Javed, I., Rafique, U., Tabassum, N., Sarfraz, M., Safi, S. Z., Ashraf, M. A. New method for the adsorption of organic pollutants using natural zeolite incinerator ash (ZIA) and its application as an environmentally friendly and cost-effective adsorbent. *Desalination and Water treatment*, 57(14), 6230- 6238. 2016.
35. Mastral, A. M., Garcia, T., Murillo, R., Callen, M. S., Lopez, M. J., Maria, V. Measurements of polycyclic aromatic hydrocarbon adsorption on activated carbons at very low concentrations. *Industrial and engineering chemistry research* 42 (1), 155-161. 2003
36. Ansari, R. And Mosayebzadeh, Z. Removal of basic dye methylene blue from aqueous solutions using sawdust and sawdust coated with polypyrrole. *Journal of the Iranian Chemical Society* (2), 339-350. 2010.
37. Ahmad, A., Ismail, S., & Bhatia, S. Optimization of coagulation– flocculation process for palm oil mill effluent using response surface methodology. *Environmental science & technology*, 39(8), 2828-2834. 2005.
38. Huang, G. B., Zhu, Q., Slew, C. Extreme learning machine: theory and applications. *Neurocomputing* 70 (1-3), 489-501. 2006.
39. Osu, C. I., & Okereke, V. Heavy metals contamination in relation to microbial counts in soils of automobile mechanic workshops, Port Harcourt Metropolis, Rivers States, Nigeria. *J. Am. Sci*, 6(9), 236-241. 2010.
40. Ibrahim, S., Ang, H.-M., & Wang, S. Removal of emulsified food and mineral oils from wastewater using surfactant modified barley straw. *Bioresource technology*, 100(23), 5744-5749. 2009.
41. Sokker, H.H., El-Sawy, N. M., Hassan, M. A., El-Anadouli, B. E. . Adsorption of crude oil from aqueous solution by hydrogel of chitosan based polyacrylamide prepared by radiation induced graft polymerization. *Journal of hazardous materials* 190 (1-3), 359-365. 2011.
42. Rajaković-Ognjanović, V., Aleksić, G., & Rajaković, L. Governing factors for motor oil removal from water with different sorption materials. *Journal of hazardous materials*, 154(1-3), 558-2008.
43. Reddy, P., Jang, S.Y., Segalman, R. A., Majumdar, A. Thermoelectricity in molecular junctions. *Science*. science.sciencemag.org. 2007.
44. Prashant Tiwari, Puravi Nayak, Shakti Ketan Prusty, Pratap Kumar Sahu. "Phytochemistry and Pharmacology of *Tinospora cordifolia*: A Review." *Systematic Reviews in Pharmacy* 9.1 (2018), 70-78. Print. doi:10.5530/srp.2018.1.14
45. Persinger, M.A. The harassment effect as pervasive out-of-body experiences: Neuroquantal evidence with more precise measurements (2010) *NeuroQuantology*, 8 (4), pp. 444-465.
46. Pradhan, R.K. Subject-Object duality and states of consciousness: A quantum mechanical approach (2010) *NeuroQuantology*, 8 (3), pp. 262-278.